

Lignovit Platin

5318

Water-based, thin-layer metallic wood glaze for industry and trade

PRODUCT DESCRIPTION

General

Water-based, thin-layer wood glaze for use in industry and trade. Special pigmentation enables spectacular, metallic shimmering colour effects. Stand-out features of this product include outstanding resistance to weathering, uniform degradation when exposed to weathering and very good block resistance.

Special properties and standards



- The coating is protected against blue stain and mould by a biocidal active substance.
Active substance:
2.4 g/kg 0.24 % 3-iodo-2-propynylbutylcarbamate
- **Proof of suitability according to DIN EN 927-2**
Confirmed by an external test certificate.
- **French ordinance DEVL1104875A**
Marking of construction coating products for their emission of volatile pollutants: A+

Application area



For non-dimensionally stable and limited dimensionally stable timber components for exterior use, such as e.g. wooden houses, timber cladding, canopies, profile boards, window shutters, balconies, gates.
Especially suitable for brushed, chipped or rough sawn wood.

PROCESSING

Processing instructions



- Please stir the product before use. However, prevent entry of air while stirring.
- The temperature of the product and object, and the room temperature must be at least +10 C.
- The optimal conditions for use are between 15 - 25 °C with a relative atmospheric humidity between 40 - 80 %.
- Do not process it under conditions of intense sunlight, rain, extremely high humidity, strong wind or pending frost.
- Early exposure to water from rain or dew must be prevented!
- For new wooden components, we recommend priming on all sides.
- Resin flow cannot be avoided by the coating application.
- Water-soluble wood extracts can be leached particularly by driving rain. This can be minimized by an all-over coating and additional sealing of the end grains.

2-0 IMC 5318 | 10/26 | replaces 1-0

ADLER-Werk Lackfabrik, Bergwerkstraße 22, A-6130 Schwaz
Fon: +43/5242/6922-190, Mail: technical-support@adler-lacke.com, www.adler-coatings.com

Our instructions are based on the current state of knowledge and are intended to advise the buyer/user to the best of our knowledge, but must be individually adapted to the areas of application and processing conditions. The buyer/user is responsible for deciding on the suitability and use of the supplied product, which is why we recommend that a sample be produced to check the suitability of the product. In all other respects, our General Terms and Conditions of Sale apply. All previous data sheets lose their validity with this edition. We reserve the right to make changes to container sizes, color shades and available gloss levels.

- Residual plaster (high level of alkalinity) or ferrous dust (rust formation) may lead to black discoloration on larch wood and other types of wood rich in extracts.
- The color shade, compatibility and adhesion to the substrate must be checked by creating sample panels.
- Ensure good ventilation during application and drying.
- Any change in the processing sequence, environmental conditions, non-observance of instructions or the use of products not listed may have an unfavourable effect on the result. Deviations lead to film and adhesion problems as well as to impairments with regard to weathering and colour shade stability.
- Please follow our **ARL 500 - Working guideline for coating non-dimensionally stable and limited dimensionally stable construction elements – General part.**

Application technique



80 -
125 ml
↓
1 m²

	Brushing	Vacuum coater
Applied quantity per application (ml/m²)	80 - 100	90 - 125

The product is ready to use.

An additional 40 % material consumption is to be expected on rough sawn timber.

The shape and surface condition of the workpiece as well as the type of application influence the actual consumption. Accurate values for consumption must be obtained by applying trial coats in advance.

Drying times

(at 23 °C and 50 % rel. humidity)



Dust-dry (ISO 1517)	approx. 30 minutes
Sandable and recoatable	approx. 3 - 4 hour(s)
Dried through	approx. 12 hour(s)

The figures given above are reference values. The drying time depends on the type of substrate, coat thickness, temperature, air exchange and relative atmospheric humidity.

Lower temperatures and/or high level of atmospheric humidity can increase the drying time.

Avoid direct sunlight!

Cleaning the working equipment



8029

With water immediately after use.

To remove dried paint residues we recommend using Clean Aqua-Cleaner (8029) (diluted 1:1 with water).

SUBSTRATE

Type of substrate

Softwoods

Substrate property

The substrate must be dry, clean, capable of holding the paint, free from separating substances such as grease, wax, silicone, resin etc. and free from wood dust, as well as tested for suitability for coating.

A prerequisite for ensuring long durability of the coating is to observe the basic principles of constructional wood preservation.

Wood moisture

15 % ± 2 %

Substrate preparation

For optimal durability we recommend to sand smooth wooden surfaces with grain size 80 – 120 in the direction of the fibre, clean thoroughly and remove wood extractives such as, for example, resins and resin pockets. Round off any sharp edges.

Clean resin-rich woods containing drying retardant components with Nitro-Verdünner 8017 (8017).

Treat algae, green deposits or mould in outdoor areas with Aviva Fungisan (8308).

COATING SYSTEM**General**

The following coating systems are exemplary.

Impregnation

If necessary outdoors, apply 1 coat of Lignovit Primo (5358) (applies to timbers of durability class 3-5 according to EN 350) to protect against blue stain, fungal decay and insect infestation.

Intermediate drying time: approx. 4 hours

Use wood preservatives safely. Always read the label and observe the respective technical data sheets of the products before use.

Please follow our **ARL 056 - Working guideline for the use of wood preservatives**.

Primer coat

1 x Lignovit Lasur (5315)

Intermediate sanding

If necessary: Slight smooth sanding: Grit size 220 – 240

Remove sanding dust.

Finishing coat

1 x Lignovit Platin (5318)

MAINTENANCE**Care**

Please follow our **ARL 504 - Working guideline for coating non-dimensionally stable and limited dimensionally stable construction elements - Maintenance and Repair**.

ORDERING INFORMATION**Size of trading unit**

4 l, 22 l

Colour shades / Glosslevels**Standard colour(s):**

Achatgrau, wie 53292 (5318053571)
 Karneolrot, wie 53319 (5318081831)
 Granatbraun, wie 53318 (5318081830)
 Topasgrau, wie 53317 (5318067251)
 Pyritgrau, wie 53316 (5318076548)
 Quarzgrau, wie 53294 (5318055716)
 Rubinrot, wie 53297 (5318053483)

Other colour shades can be obtained using the **ADLER colour mixing system ADLERMix**.

Base paint(s):

Lignovit Platin Basis W30 (5318000030)

It is recommended to prepare a trial colour sample on the original substrate using the coating system selected in order to assess the final colour shade.

In order to ensure uniformity of the colour shade, use only material with the same batch number on a given surface.

Please consume blended products within 3 months.

Please observe our **ARL 800 - Working guideline for working (including care and maintenance) with ADLER Mix, PUR Mix and Color4You dosing machines.**

Supplementary products

Clean Aqua-Cleaner 8029 (8029)
Lignovit Lasur (5315)
Aviva Fungisan (8308)
Lignovit Primo (5358)
Nitro-Verdünnern 8017 (8017)

Please refer to the corresponding technical data sheets of the products.

FURTHER DETAILS

Durability / storage



Min. 1 year(s) in the original sealed containers.

Make sure the product is protected against moisture, direct sunlight, frost and high temperatures (above 30 °C).

Close opened containers well and use up the content as soon as possible.

Technical specifications

VOC content of the ready-to-use mixture: Limit value according to Directive 2004/42/EC for Lignovit Platin (Cat A/d): 130 g/l.
Lignovit Platin contains a maximum of 30 g/l VOC.

Giscode

BSW50

Safety information



The product is only suitable for the industrial and professional use.

When sanding, use at least a P2 dust filter as personal safety equipment to protect against abrasive and wood dust.

Further information on the subject of safety during transport, storage and handling as well as disposal can be found in the relevant safety data sheet. The current version can be accessed on the Internet at **www.adler-lacke.com**.