

## Bluefin Pigmorapid G30

3553

Water-based pigmented paint for furniture and interior finishing, for industrial use

### PRODUCT DESCRIPTION

#### General

Water-based **1C pigmented furniture paint**, dries very quickly and offers good mechanical and chemical resistance. Stand-out features of this product include excellent resistance to the effects of light, good filling performance and good stability on vertical surfaces.

#### Special properties and standards



- **ÖNORM A 1605-12 (furniture surfaces)**  
Resistance to chemical reactions: 1-C  
Response to abrasion: 2-D ( $\geq 50$  U)  
Response to scratches: 4-E ( $\geq 0.5$  N)  
Flame treatment: 5-B (highly non-flammable furniture surfaces)



- **DIN 68861 (furniture surfaces)**  
Part 1: Response to chemical stress: 1 C  
Part 2: Response to abrasion: 2 D ( $> 50$  to  $\leq 150$  U)  
Part 4: Response to scratches: 4 E ( $> 0.5$  to  $\leq 1.0$  N)



- **ÖNORM A 3800-1 (fire behaviour)**  
In conjunction with a flame-retardant substrate:  
flame-retardant, Q1, Tr 1



- **ÖNORM EN 71-3**  
Safety of toys; migration of certain elements (free of heavy metals)



- **DIN 53160-1 and DIN 53160-2**  
Perspiration and saliva-proof properties



- **French ordinance DEVL1104875A**  
Marking of construction coating products for their emission of volatile pollutants: A+

#### Application area



For lightly stressed/subordinate and normally stressed parts of the living area such as bedrooms and living rooms in furniture and interior fittings: Application areas III - IV in accordance with ÖNORM A 1610-12.


This product is also suitable for large-scale industrial coating.

For upright surfaces and for profiled workpieces and battens.

For hardly inflammable or flame-retardant coating systems.


## PROCESSING

### Processing instructions



- Please stir the product before use.
- The temperature of the product and object, and the room temperature must be at least + 15 °C.
- For surfaces that are subject to especially heavy wear (tables, chairs, etc.), we generally recommend a topcoat of Bluefin Top-Antiscratch (2960) (chemical resistance – 1-B1 in accordance with ÖNORM A 1605-12 Test 1 – also in the colour RAL 9010 "Pure white (Reinweiß)" or Bluefin Resist (2963). Allows you to achieve surfaces that are ring test-resistant (resistant to metal marking) and offer very good mechanical resistance.
- When coating interior doors, it must be ensured that only sealing profiles compatible with acrylic paints are used.
- When using plastic edgebands, an adhesion test must always be carried out with the planned structure. Adhesion can be improved on ABS edgebands by using ABS Kantenaktivator (8315000210).
- Any change in the processing sequence, environmental conditions, non-observance of instructions or the use of products not listed may have an unfavourable effect on the result.
- Please follow our **ARL 150 - Working guidelines for water-based furniture coatings**.

### Application technique



	Airless	Airless air-supported (Airmix®, Aircoat, etc.)	Cup gun
Spraying nozzle Ø (mm)	0,23 - 0,33		2,0
Spraying pressure (bar)	100 - 120	80 - 100	2 - 3
Vaporizer Air (bar)	-	1 - 2	-
Diluent	Water		
Diluent amount added (%)	-		0 - 5
Applied quantity per application (g/m²)	120 - 200*		
Total quantity applied (g/m²)	max. 450		

\*closed-pore surfaces: approx. 130  
 open-pore coating systems in pastel shades and RAL 9010: approx. 150 – 200  
 open-core coating systems in solid colours approx. 120 – 150

The shape and surface condition of the workpiece as well as the type of application influence the actual consumption. Accurate values for consumption must be obtained by applying trial coats in advance.

### Drying times

(at 23 °C and 50 % rel. humidity)



Can be sanded and then coated with

Bluefin Pigmorapid G30 (3553) after: approx. 2 h Can be painted over with, for example Bluefin Top-Antiscratch (2960)

or Bluefin Resist (2963) after: at least 12 hours

max. 3 days

The figures given above are reference values. Drying depends on the substrate, layer thickness, temperature, air exchange, relative humidity, stacking pressure and stacking conditions.

Lower temperatures and/or high level of atmospheric humidity can increase the drying time.

## Cleaning the working equipment



8029

With water immediately after use.

To remove dried paint residues we recommend using Aqua-Cleaner (8029) (diluted 1:1 with water).

## SUBSTRATE

### Type of substrate

Solid wood, chipboard or wood fibre materials suitable for opaque varnishing, veneered or coated with priming film.

### Substrate property

The substrate must be dry, clean, capable of holding the paint, free from separating substances such as grease, wax, silicone, resin etc. and free from wood dust, as well as tested for suitability for coating.

### Substrate preparation

#### Wood sanding:

Grit size 150 – 180

#### Carrier plates coated with priming film:

Grit size 180 - 240

## COATING SYSTEM

### Primer coat

#### For closed-pore coating surfaces

**Chipboard or MDF boards** with film depending on the quality requirements (filling performance, evenness of the surface) without priming or 1 x Bluefin Isospeed (3134) in the corresponding colour

#### **Solid wood or chipboard panels veneered with blind veneer (e. g. beech):**

2 x Bluefin Isospeed (3134) or Aqua-Isospeed Thix (3119)

#### **MDF panels:**

2 - 3 x Bluefin Isospeed (3134) + 5 % Aqua-Hardener 8450 (8450) or Aqua-Isospeed Thix (3119) + 5 % Aqua-Hardener 8450 (8450) or Alternatively: 1 x pre-insulated with Bluefin Unistar (2965) and 2 x primed with Bluefin Isospeed (3134)

#### For open-pore coating surfaces

Pre-insulation with 150 - 200 g/m<sup>2</sup> Bluefin Isospeed (3134) + 5 % Aqua-Hardener 8450 (8450) with woods that are susceptible to resin flow (e.g. pine) woods that contain water-soluble discolouring substances (e.g. ash) coating systems in the colour RAL 9010 "Pure white (Reinweiß)" and in pastel shades

Drying overnight at room temperature.

### Intermediate sanding



Grit size 280 – 360

Avoid sanding straight through!

Remove sanding dust.

### Topcoat

1 x Bluefin Pigmorapid G30 (3553)

## CLEANING AND MAINTENANCE

### Cleaning and Maintenance

Cleaning with Clean-Möbelreiniger (7202) and care with Clean-Möbelpflege Plus (7222).

## ORDERING INFORMATION

### Size of trading unit

22 kg

### Colour shades / Glosslevels

#### Standard colour(s):

W10 Weiß, tönbar (3553000010)

RAL9016 Verkehrsweiß (3553009016)

Special colours on request.

### Supplementary products

ABS Kantenaktivator (8315)

Aqua-Cleaner 8029 (8029)

Aqua-Hardener 8450 (8450)

Aqua-Isospeed Thix (3119)

Bluefin Isospeed (3134)

Bluefin Resist (2963)

Bluefin Top-Antiscratch (2960)

Bluefin Unistar (2965)

Clean-Möbelpflege Plus (7222)

Clean-Möbelreiniger (7202)

Please refer to the corresponding technical data sheets of the products.

## FURTHER DETAILS

### Durability / storage



Min. 9 month(s) in the original sealed containers.

Cool, but frost-free.

### Technical specifications

Delivery viscosity: 110 second – 120 second according to DIN 53211  
(6 mm measuring cup, 20 °C)

### Safety information



The product is only suitable for industrial use.

The inhalation of paint aerosols during spray application must generally be avoided. This is ensured by the proper use of a respirator (combination filter A2/P2).

Further information on the subject of safety during transport, storage and handling as well as disposal can be found in the relevant safety data sheet. The current version can be accessed on the Internet at **[www.adler-lacke.com](http://www.adler-lacke.com)**.