

Aqua-Hardener 8249 PRO

8249

Hardener for water-based ADLER paints/varnishes for windows and exterior doors, for use in industry and trade

PRODUCT DESCRIPTION

Product numbers

8249000210



General

Isocyanate-free hardener formulated with a polymeric aziridine. With a pot life of 24 hours, ensures flexibility and versatility in the application process.

Application area



For dimensionally stable timber components for exterior and interior use, such as e.g. wooden windows and front doors.

Windows and front doors made of PVC and other synthetic material suitable for coating.

PROCESSING

Processing instructions



- Please stir the product before use.
- Immediately after adding Aqua-Hardener 8249 PRO (8249) to the paint component, blend in carefully.
- Mixed paints and stains must be processed as specified in the corresponding technical data sheet.
- Do not close containers with hardened material.
- Any change in the processing sequence, environmental conditions, non-observance of instructions or the use of products not listed may have an unfavourable effect on the result. Deviations lead to film and adhesion problems as well as to impairments with regard to weathering and color stability.

Blending ratio

100 parts by weight of coating component
7 parts by weight Aqua-Hardener 8249 PRO (8249)

Aqua-Hardener 8249 PRO (8249) can be used in the following products:

Aquawood Diamond-Sealer D (5520)
Aquawood Diamond-Sealer L (5723)
Aquawood Diamond-Top D (5090)
Aquawood Diamond-Top L (5196)
Aquawood Diamond Pearl (5091)
Aquawood Protor-Base D (5806)
Aquawood Protor-Base L (5807)
Aquawood Protor-Finish D (5808)
Aquawood Protor-Finish L (5809)
Aquawood Protor-Finish Pearl (5804)
Aquawood Intercare Isogrip (5505)
Polycolor Pro 2K (5086)
Polycolor Pro 2K Pearl (5085)
Polycolor Top 2K (5082)
Polycolor Top 2K Metallic (5080)
Polycolor Top 2K VAC (5083)
Polycolor Top 2K VAC Metallic (5081)

The products can only be used with the hardener Aqua-Hardener 8249 PRO (8249) and in the mixing ratio specified. Deviations lead to film and adhesion problems.

After addition of hardener, a waiting time of approx. 10 minutes is recommended for improved degassing.

Please refer to the corresponding technical data sheets of the products.

Pot life


24 hour(s)

A further extension of the pot life is not possible.

Increased temperatures reduce the pot life.

ORDERING INFORMATION**Size of trading unit**

280 g, 770 g, 1.1 kg, 9 kg

FURTHER DETAILS**Durability / storage**

Min. 6 month(s) in the original sealed containers.

Make sure the product is protected against moisture, direct sunlight, frost and high temperatures (above 30 °C).

Immediately seal the container to prevent humidity from penetrating.

Close opened containers well and use up the content as soon as possible.

Safety information

The product is only suitable for the industrial and professional use.

Further information on the subject of safety during transport, storage and handling as well as disposal can be found in the relevant safety data sheet. The current version can be accessed on the Internet at www.adler-lacke.com.