

Aquawood Covatop XT 20

5020

Water-based, **matt, opaque finishing coat** for **wooden windows and exterior doors**, for use in industry and trade

Optimised for a **3-layer coating system**

PRODUCT DESCRIPTION

General

Water-based, matt, pigmented finishing coat with outstanding weathering resistance and permanent elasticity. Stand-out features of this product include very good block resistance, very good impact strength, rapid establishment of water resistance, short drying times, a natural look and a pleasant feel. Good non-sag properties on vertical surfaces and optimal flow. Particularly low number of micro-bubbles during airless spray application due to highly active defoaming agents/deaerators.

Special properties and standards



- **ADLER green product**
ADLER green products are objectively tested and certified according to three categories: Environment, Health & Safety, and Durability. Only products that score positively in all these areas are awarded the green sustainability label.



- **Proof of suitability according to DIN EN 927-2**
Confirmed by an external test certificate.



- **DIN 53160-1 and DIN 53160-2**
Perspiration and saliva-proof properties



- **ÖNORM EN 71-3**
Confirmed by an external test certificate.
Safety of toys; migration of certain elements (free of heavy metals).



- **declared product in baubook**
Criteria of the "Baubook Ökologisch ausschreiben" fulfilled



- **French ordinance DEVL1104875A**
Marking of construction coating products for their emission of volatile pollutants: A+

- **AgBB-scheme 2018/2021 Committee for Health-related Evaluation of Building Products (AgBB)**

When used properly in accordance with the technical data sheet, the product fulfils the requirements of AgBB scheme 2018/2021 Committee for Health-related Evaluation of Building Products (AgBB)

Application area


For dimensionally stable timber components for exterior and interior use, such as e.g. wooden windows and front doors.

For humid rooms (e.g. indoor swimming pools) only with a special build-up.

For non-dimensionally stable timber components in the outdoor area we recommend for example Pullex Color (4403) or Pullex Aqua-Color (5325).

PROCESSING**Processing instructions**

- Please stir the product before use. However, prevent entry of air while stirring.
- The temperature of the product and object, and the room temperature must be at least + 15 °C.
- The optimal conditions for use are between 15 - 25 °C with a relative atmospheric humidity between 40 - 80 %.
- Too high dry film thicknesses from approx. 120 µm reduce the diffusion capacity and should thus be avoided.
- Sealants must be compatible with the coat and may only be applied once the paint has dried through. Sealing profiles with plasticizers tend to stick together in combination with paints. Please only use those types that have been tested.
- When changing from Aquawood Covatop XT 20 (5020) to other water-based paint systems, care must be taken to adequately clean the pipes and spray equipment, preferably with warm water.
- Any change in the processing sequence, environmental conditions, non-observance of instructions or the use of products not listed may have an unfavourable effect on the result. Deviations lead to film and adhesion problems as well as to impairments with regard to weathering and color stability.
- Please follow our **ARL 300 - Working guideline for coating dimensionally stable and limited dimensionally stable construction elements - General part** along with all standards and guidelines for window construction.

Application technique

	Airless	Airless air-supported (Airmix®, Aircoat, etc.)
Spraying nozzle Ø (mm)	0,28 - 0,33	
Spray nozzle (Ø inch)	0,011 - 0,013	
Nozzle angle (°)	20 - 40	
Spraying pressure (bar)	80 - 100	
Vaporizer Air (bar)	-	0,5 - 1,5
Spraying distance (cm)	25	
Diluent	Water	
Diluent amount added (%)	0 - 5	
Applied quantity per application (ml/m²)	150 - 300	
Wet film (µm)	150 - 300	
Dry film complete coating system (µm)	min. 100	

The shape and surface condition of the workpiece as well as the type of application influence the actual consumption. Accurate values for consumption must be obtained by applying trial coats in advance.

Drying times

(at 23 °C and 50 % rel. humidity)

Dust-dry (ISO 1517)	approx. 1 hour(s)
Tack-free	approx. 3 hour(s)


Stackable with PE fine foam spacers at room temperature	approx. 5 hour(s)
Stackable with PE fine foam spacers after forced drying 20 minutes Evaporation/dripping zone 90 minutes drying stage (35 - 40 °C) 20 minutes cooling stage	approx. 130 minutes

The figures given above are reference values. The drying time depends on the type of substrate, coat thickness, temperature, air exchange and relative atmospheric humidity.

Lower temperatures and/or high level of atmospheric humidity can increase the drying time.

Avoid direct sunlight!

Cleaning the working equipment



With water immediately after use.

To remove dried paint residues we recommend using Clean Aqua-Cleaner (8029) (diluted 1:1 with water).

SUBSTRATE

Type of substrate

Wood in accordance with the guidelines for window construction.

Substrate property

The substrate must be dry, clean, capable of holding the paint, free from separating substances such as grease, wax, silicone, resin etc. and free from wood dust, as well as tested for suitability for coating.

Wood moisture

13 % ± 2 %

COATING SYSTEM

General

The following coating systems are exemplary.

Impregnation

1 x AquaWood Primo A2 (5452)

Intermediate drying time: approx. 4 hours

Use wood preservatives safely. Always read the label and observe the respective technical data sheets of the products before use.

Please follow our **ARL 056 - Working guideline for the use of wood preservatives**.

Intermediate coat

1 x AquaWood Intercare ISO (5503)

or

1 x AquaWood Intercare SQ (5522)

or

1 x AquaWood Intercare ES (5501)

Intermediate drying time: approx. 4 hours

Intermediate sanding



Grit size 220 – 240

Remove sanding dust.

Finishing coat

1 x AquaWood Covatop XT 20 (5020)

For front doors

To achieve optimal chemical and mechanical resistance, an additional application of Aquawood Protect (5128) (colourless two-component clear coating) is recommended, or alternatively the use of the Aquawood Protor or Aquawood Dura system. Deviations from this system recommendation may lead to reduced surface resistance.

MAINTENANCE**Care**

The durability depends on several factors: these include particularly the type of weathering, constructive protection, mechanical stress and the choice of colour applied. To obtain long durability, regular inspection, maintenance and, if necessary, repair measures are necessary.

Annual cleaning with Top-Cleaner (7208) and maintenance with Top-Care (7227) in the package with Windoor Care-Set (7229).

Maintenance

Please follow our **ARL 304 - Working guideline for coating dimensionally stable and limited dimensionally stable construction elements - Maintenance and repair.**

ORDERING INFORMATION**Size of trading unit**

5 kg, 10 kg, 20 kg, 120 kg poly drum

Colour shades / Glosslevels**Standard colour(s):**

RAL9010 Reinweiß (5020009010)

RAL9016 Verkehrsweiß (5020009016)

Other colour shades can be obtained using the **ADLER colour mixing system ADLERMix.**

Base paint(s):

Aquawood Covatop XT 20 W10 Weiß, tönbar (5020000010)

Aquawood Covatop XT 20 Basis W30 (5020000030)

In order to ensure uniformity of the colour shade, use only material with the same batch number on a given surface.

It is recommended to prepare a trial colour sample on the original substrate using the coating system selected in order to assess the final colour shade.

Please observe our **ARL 800- Working guideline for working (including care and maintenance) with ADLER Mix, PUR Mix and Color4You dosing machines.**

Supplementary products

Clean Aqua-Cleaner 8029 (8029)

Aquawood Intercare ES (5501)

Aquawood Intercare ISO (5503)

Aquawood Intercare SQ (5522)

Aquawood Primo A2 (5452)

Aquawood Protect (5128)

Pullex Aqua-Color (5325)

Pullex Color (4403)

Top-Care (7227)

Top-Cleaner (7208)

Windoor Care-Set (7229)

Please refer to the corresponding technical data sheets of the products.

FURTHER DETAILS**Durability / storage**

Min. 1 year(s) in the original sealed containers.

Make sure the product is protected against moisture, direct sunlight, frost and high temperatures (above 30 °C).

Close opened containers well and use up the content as soon as possible.

Technical specifications	VOC content of the ready-to-use mixture: Limit value according to Directive 2004/42/EC for Aquawood Covatop XT 20 (Cat A/d): 130 g/l. Aquawood Covatop XT 20 contains a maximum of 70 g/l VOC.
Giscode	BSW30
DGNB (German Sustainable Building Council)	Quality level 4 (with factory coating)
Safety information 	The product is only suitable for the industrial and professional use. When sanding, use at least a P2 dust filter as personal safety equipment to protect against abrasive and wood dust. In case of hardwood (especially for Beech, Oak) a dust filter P3 is recommended. The inhalation of paint aerosols during spray application must generally be avoided. This is ensured by the proper use of a respirator (combination filter A2/P2). Further information on the subject of safety during transport, storage and handling as well as disposal can be found in the relevant safety data sheet. The current version can be accessed on the Internet at www.adler-lacke.com.