

Aquawood Primo TG WF

5462

Water-based wood primer without any biocidal agents for wooden windows and exterior doors, for use in industry and trade

Optimised for a 3-layer coating system

PRODUCT DESCRIPTION

General


Water-based, ready-to-use wood primer which offers especially good coverage of softwood edges. Stand-out features of this product include excellent resistance to sagging on both hardwoods and softwoods and an insulating effect when using the colour White. Contains highly effective light stabilisers to absorb UV radiation and stabilise the lignin in the wood.

Special properties and standards



- **ADLER green product**
ADLER green products are objectively tested and certified according to three categories: Environment, Health & Safety, and Durability. Please also refer to the sustainability data sheet.
- **Declared in baubook**
Product has been declared and validated
- **French ordinance DEVL1104875A**
Marking of construction coating products for their emission of volatile pollutants: A+

Application area



For dimensionally stable and limited dimensionally stable timber components for exterior and interior use, such as e.g. wooden windows, front doors, window shutters, gates, winter garden.

For coating systems where preventive chemical wood protection in accordance with DIN 68800 or ÖNORM B3802-3 is not required.

Preventive chemical wood protection is not required for wood species in durability classes 1 and 2 (according to DIN EN 350).

A waiver of preventive chemical wood protection for wood of durability class 3 - 5 (according to EN 350) must be agreed in writing (please observe national standards/guidelines). Non-compliance can lead to conflicts with normative specifications or legal requirements.

PROCESSING

Processing instructions



- Please stir the product before use. However, prevent entry of air while stirring.
- The temperature of the product and object, and the room temperature must be at least + 15 °C.
- The optimal conditions for use are between 15 - 25 °C with a relative atmospheric humidity between 40 - 80 %.
- The product is not weather-resistant without a topcoat!
- In case of flow coating for a long time, the pH-value reduces and, as a result, there could be sagging problems. Hence, the pH value of impregnations that have already been used must be checked and, if required, corrected to the target pH-value of 9 – 9.5 by adding approx. 0.10 % of Neutralisationsmittel 9125 (96149) (the addition of 0.10 % will increase the pH-value up to approx. 0.6 units).
- If the viscosity increases as a result of evaporation, it must be compensated with water (set viscosity: 45 – 51 seconds in a 2 mm-measuring-cup) Before measuring the wood dust has to be screened.
- If foam forms in the flooding system, an addition of 0.1 - 0.3 % of Entschäumer-Lösung für Aquawood TIG (90642) or Entschäumer-Lösung (90643) is recommended.
- Any change in the processing sequence, environmental conditions, non-observance of instructions or the use of products not listed may have an unfavourable effect on the result. Deviations lead to film and adhesion problems as well as to impairments with regard to weathering and color stability.
- Please follow our **ARL 300 - Working guideline for coating dimensionally stable and limited dimensionally stable construction elements - General part** along with all standards and guidelines for window construction.

Application technique



	Flow coating	Immersion
Applied quantity per application (ml/m²)	100 - 125	

The product is ready to use.

The shape and surface condition of the workpiece as well as the type of application influence the actual consumption. Accurate values for consumption must be obtained by applying trial coats in advance.

Drying times

(at 23 °C and 50 % rel. humidity)




Re-coatable at room temperature	approx. 4 hour(s)
Re-coatable after forced drying 20 minutes draining 50 minutes drying stage (35 - 40 °C) 20 minutes cooling stage	approx. 90 minutes

The figures given above are reference values. The drying time depends on the type of substrate, coat thickness, temperature, air exchange and relative atmospheric humidity.

Lower temperatures and/or high level of atmospheric humidity can increase the drying time.

Avoid direct sunlight!

Cleaning the working equipment



With water immediately after use.

To remove dried paint residues we recommend using Clean Aqua-Cleaner (8029) (diluted 1:1 with water).

SUBSTRATE	
Type of substrate	Wood in accordance with the guidelines for window construction.
Substrate property	The substrate must be dry, clean, capable of holding the paint, free from separating substances such as grease, wax, silicone, resin etc. and free from wood dust, as well as tested for suitability for coating. A prerequisite for ensuring long durability of the coating is to observe the basic principles of constructional wood preservation.
Wood moisture	13 % ± 2 %
Substrate preparation	Wood sanding: Hardwoods: Grit size 150 - 180 Softwoods: Grit size 100 - 150
COATING SYSTEM	
General	The following coating systems are exemplary.
Primer coat	Transparent: 1 x Aquawood Primo TG WF (5462) in the desired colour Opaque: 1 x Aquawood Primo TG WF (5462) white
Intermediate coat	Transparent: Softwoods: 1 x Aquawood Intermedio DQ (5706) or 1 x Aquawood Intermedio DQ WF (5719) Hardwoods and Larch: 1 x Aquawood Intermedio ISO (5705) Intermediate drying: approx. 2 hour(s) Opaque: 1 x Aquawood Intercare ISO (5503) or 1 x Aquawood Intercare SQ (5522) or 1 x Aquawood Intercare ES (5501) Intermediate drying time: approx. 4 hours
Intermediate sanding	Grit size 220 – 240 Remove sanding dust.
Finishing coat	Transparent: 1 x Aquawood Finatop 40 (5140) or 1 x Aquawood Finapro 20 (5101)



Opaque:

1 x Aquawood Covatop XT 20 (5020)

or

1 x Aquawood Covapro 20 (5023)

For front doors

To achieve optimal chemical and mechanical resistance, an additional application of Aquawood Protect (5128) (colourless two-component clear coating) is recommended, or alternatively the use of the Aquawood Protor or Aquawood Dura system. Deviations from this system recommendation may lead to reduced surface resistance.

ORDERING INFORMATION

Size of trading unit

4 l, 22 l und 120 l (White)

Colour shades / Glosslevels



Standard colour(s):

Weiß (5462050000)

Softweiß H/A (5462070448)

Other colour shades can be obtained using the **ADLER colour mixing system ADLERMix**.

Base paint(s):

Aquawood Primo TG WF Basis W30 (5462000030)

Aquawood Primo TG WF Basis W40 (5462000040)

The final colour is basically obtained from the inherent colour of the wood, the applied quantity, the colour of the impregnation and the colour of the finishing coat.

In order to ensure uniformity of the colour shade, use only material with the same batch number on a given surface.

It is recommended to prepare a trial colour sample on the original substrate using the coating system selected in order to assess the final colour shade.

In order to lay particular emphasis on the wood structure, the colour shade of Aquawood Primo TG WF selected should be darker than the one of the top-coat.

Please observe our **ARL 800- Working guideline for working (including care and maintenance) with ADLER Mix, PUR Mix and Color4You dosing machines**.

Supplementary products

Clean Aqua-Cleaner 8029 (8029)

Aquawood Covapro 20 (5023)

Aquawood Covatop XT 20 (5020)

Aquawood Finapro 20 (5101)

Aquawood Finatop 40 (5140)

Aquawood Intercare ES (5501)

Aquawood Intercare ISO (5503)

Aquawood Intercare SQ (5522)

Aquawood Intermedio DQ (5706)

Aquawood Intermedio DQ WF (5719)

Aquawood Intermedio ISO (5705)

Aquawood Protect (5128)

Entschäumer-Lösung (90643)

Entschäumer-Lösung für Aquawood TIG (90642)

Neutralisationsmittel 9125 (96149)

Please refer to the corresponding technical data sheets of the products.

FURTHER DETAILS

Durability / storage



Min. 1 year(s) in the original sealed containers.

Make sure the product is protected against moisture, direct sunlight, frost and high temperatures (above 30 °C).

Close opened containers well and use up the content as soon as possible.

Technical specifications

VOC content of the ready-to-use mixture: Limit value according to Directive 2004/42/EC for Aquawood Primo TG WF (Cat A/f): 130 g/l.
Aquawood Primo TG WF contains a maximum of 80 g/l VOC.

Giscode

BSW30

DGNB (German Sustainable Building Council)

Quality level 4 (with factory coating)

Safety information



The product is only suitable for the industrial and professional use.

When sanding, use at least a P2 dust filter as personal safety equipment to protect against abrasive and wood dust. In case of hardwood (especially for Beech, Oak) a dust filter P3 is recommended.

Further information on the subject of safety during transport, storage and handling as well as disposal can be found in the relevant safety data sheet. The current version can be accessed on the Internet at www.adler-lacke.com.