

Aviva Tiefengrund LM

4080

Solvent-based **primer for exterior use** for DIY and professional use

PRODUCT DESCRIPTION

General

Solvent-based, transparent primer for priming porous, extremely absorbent and sandy mineral substrates. Alkali-resistant and frost-resistant. It stabilises heavily sandy or slightly chalky surfaces and equalises substrates with extremely high or uneven absorbency. The product is characterised by excellent penetration properties and high water vapour permeability.

Application area



For absorbent and sandy mineral substrates such as plasters or concrete, etc., in exterior areas.


PROCESSING

Processing instructions



- Please stir and shake the product well before use.
- The temperature of the product and object, and the room temperature must be at least + 5 °C.
- The optimal conditions for use are between 15 - 25 °C with a relative atmospheric humidity between 40 - 80 %.
- Application preferably with a brush or scrubbing brush.
- In case of highly absorbent and sandy plaster substrates, if necessary apply two preliminary coats using the wet-on-wet method.
- A glossy finish must be avoided under all circumstances.
- Aviva Tiefengrund LM must be able to penetrate deeply into the substrate.
- Carefully cover and mask areas which are not to be coated. Remove paint splashes immediately using Adlerol-Verdünner 7231 (7231).
- Any change in the processing sequence, environmental conditions, non-observance of instructions or the use of products not listed may have an unfavourable effect on the result.

Application technique



	Brushing
Applied quantity per application (ml/m ²)	150 - 200
Yield per application (m ² /l)	6 - 9

The shape and surface condition of the workpiece as well as the type of application influence the actual consumption. Accurate values for consumption must be obtained by applying trial coats in advance.

Drying times

(at 23 °C and 50 % rel. humidity)

**24h**

Subsequent coating

approx. 24 hour(s)

The figures given above are reference values. The drying time depends on the type of substrate, coat thickness, temperature, air exchange and relative atmospheric humidity.

Lower temperatures and/or high level of atmospheric humidity can increase the drying time.

Avoid direct sunlight!

Cleaning the working equipment**7231**

With Adlerol-Terpentinölersatz (7231) immediately after use.

SUBSTRATE**Type of substrate**

For sandy and absorbent mineral substrates such as plasters or concrete, etc.

Substrate property

The substrate must be dry, clean, capable of holding the paint, free from separating substances such as grease, wax, silicone, etc. and free from dust, as well as tested for suitability for coating.

Please observe the additional documents:

- ÖNORM B 2230-2
- ÖNORM B 3430-1
- DIN 18363
- Current BFS information sheets

Substrate preparation

No pre-treatment is necessary for clean, dry and sound substrates.

Remove old coatings that cannot be recoated.

Touch up small cracks, holes or unevenness using a suitable filler. Sand off filler burrs and remove the dust thoroughly.

Allow fresh plaster, concrete and screed to dry thoroughly for at least 4 weeks. Re-plastered patches must be set well and dried up. If necessary, treat with fluosilicate. Clean concrete surfaces with dirt deposits, separating agents or powder layers mechanically or with the help of pressurised water jets (in compliance with statutory regulations).

Thoroughly remove greasy or oily impurities using Clean Multi-Entfetter (7233).

Treat algae, green deposits or mould in outdoor areas with Aviva Fungisan (8308).

COATING SYSTEM**Primer coat**

1 x Aviva Tiefengrund LM (4080)

Intermediate/finishing coat

Aviva Acryl-Color (4084)

ORDERING INFORMATION**Size of trading unit**

750ml, 5l

Colour shades	Standard colour(s): Farblos (4080000200)
Supplementary products	Adlerol-Verdünnern 7231 (7231) Clean Multi-Entfetter (7233) Aviva Fungisan (8308) Please refer to the corresponding technical data sheets of the products.
FURTHER DETAILS	
Durability / storage 	Min. 3 year(s) in the original sealed containers. Make sure the product is protected against moisture, direct sunlight, frost and high temperatures (above 30 °C). Close opened containers well and use up the content as soon as possible.
Technical specifications	VOC content of the ready-to-use mixture: Limit value according to Directive 2004/42/EC for Aviva Tiefengrund LM (Cat A/h): 750 g/l. Aviva Tiefengrund LM contains a maximum of 730 g/l VOC.
Giscode	BSL50
Declaration of ingredients according to VdL-RL 01	acrylic resins / aliphatic compounds / coat binding agent
Safety information 	Only dispose of empty containers for recycling, liquid material residues can be disposed of as water-based paint waste, dried material residues as hardened paint or as household waste. Further information on the subject of safety during transport, storage and handling as well as disposal can be found in the relevant safety data sheet. The current version can be accessed on the Internet at www.adler-lacke.com .