

Aviva Tiromin-Color

4066

Tintable, premium silicate interior paint without the addition of preservatives for DIY and professional use

PRODUCT DESCRIPTION

General

Coloured, non-film-forming, odour-neutral interior paint based on potassium water glass with organic stabilisers. This easy-to-use and efficient product is formulated without any addition of solvents, plasticisers, fogging-active substances or preservatives.

Special properties and standards



- **DIN EN 52615**
High level of diffusion



- **ÖNORM EN 13300**
Wet abrasion resistance: R-class 2
Contrast ratio (covering power): H₁₀-class 2 for 7 m²/l)
Gloss level: G4 dull matt
Maximum grit size: S1 fine



- **French ordinance DEVL1104875A**
Marking of construction coating products for their emission of volatile pollutants: A+

Application area




For mineral coatings in the entire residential sector, schools and kindergartens, public buildings, as well as in the field of monument preservation.

Particularly suitable for mineral substrates and stable silicate coatings.

PROCESSING


Processing instructions



- Please stir the product before use.
- A product, object and room temperature of at least + 8 °C is required.
- The optimal conditions for use are between 15 - 25 °C with a relative atmospheric humidity between 40 - 80 %.
- Ensure good ventilation to allow the coating to set.
- To avoid crusts apply the coat at one stroke using the wet-on-wet method.
- Blend the brush-painted areas well and then roll the surface in one direction.

- Signs of touch-up work on the surface depend on several factors and hence, cannot be avoided (BFS data sheet 25).
- Material with the same consistency and batch number as well as the same tools must be used for repairs to the surface.
- The color shade, compatibility and adhesion to the substrate must be checked by creating sample panels.
- When reworking sealants, cracks and discoloration may occur in the coating material. Due to the large number of sealant systems, you should carry out your own tests in individual cases to assess adhesion and processing results.
- Carefully cover and mask areas which are not to be coated. Remove paint splashes immediately with water.
- Any change in the processing sequence, environmental conditions, non-observance of instructions or the use of products not listed may have an unfavourable effect on the result.

Application technique

0-5% H₂O

1l
↓
7 m²

	Airless	Brushing	Rolling
Spraying nozzle Ø (mm)	0,53 - 0,63	-	-
Spray nozzle (Ø inch)	0,021 - 0,026	-	-
Nozzle angle (°)	50	-	-
Spraying pressure (bar)	150 - 180	-	-
Fine strainer (µm)	200	-	-
Diluent	Water		
Diluent amount added (%)	0 - 5		
Applied quantity per application (ml/m ²)	ca. 145		
Yield per application (m ² /l)	ca. 7		

The shape and surface condition of the workpiece as well as the type of application influence the actual consumption. Accurate values for consumption must be obtained by applying trial coats in advance.

Drying times

(at 23 °C and 50 % rel. humidity)



Subsequent coating	approx. 12 hour(s)
--------------------	--------------------

The figures given above are reference values. The drying time depends on the type of substrate, coat thickness, temperature, air exchange and relative atmospheric humidity.

Lower temperatures and/or high level of atmospheric humidity can increase the drying time.

Cleaning the working equipment



With soap-water immediately after use.

To remove dried product residues we recommend using Clean Abbeizer-Express (8313).

SUBSTRATE

Type of substrate

Mineral substrates (plaster, concrete), plasterboard, stable silicate paint coats.

Substrate property

The substrate must be dry, clean, capable of holding the paint, free from separating substances such as grease, wax, silicone, etc. and free from dust, as well as tested for suitability for coating.

Remove old coatings that cannot be recoated.

Please observe the additional documents:

- ÖNORM B 2230-2
- ÖNORM B 3430-1
- DIN 18363
- Current BFS information sheets

Substrate preparation

Touch up small cracks, holes or unevenness using a suitable filler.

Thoroughly remove greasy or oily impurities using Clean Multi-Entfetter (7233).

No pre-treatment is necessary for clean, slightly absorbent, dry and recoatable substrates.

Treat mold infestation indoor with Aviva Schimmelex chlorfrei (8312) or Aviva Fungisan (8308).

Plasters of mortar groups P I, P II and P III

Allow new plaster application to remain untreated for 3 to 4 weeks. Re-plastered patches must be set well and dried up. If necessary, treat with fluosilicate.

On coarsely porous, slightly sanding or absorbent surfaces, prime with Aviva Silikat-Primer (4079) diluted 1:1 with water.

In the case of highly absorbent and sanding plaster substrates, apply two coats of Aviva Silikat-Primer (4079) diluted 1:1 with water, wet on wet.

Gypsum and ready made plasters in mortar groups P IV and P V:

Grind off any sintered coat remaining.

On coarsely porous, slightly sanding or absorbent surfaces, prime with Aviva Silikat-Primer (4079) diluted 1:1 with water.

Gypsum plaster boards (GKP):

Sand off filler burrs and remove the dust thoroughly.

Base coat with Aviva Tiefengrund WV (4074) diluted 1:1 with water.

For panels with water-soluble, discoloring ingredients, an additional primer coat with e.g. Aviva Isolier-Weiß CT (4049) is required. Please observe BFS data sheet no. 12.

Concrete surfaces:

If there are deposits of dirt, separating agents or chalky layers, the surface should be mechanically cleaned.

On coarsely porous, slightly sanding or absorbent surfaces, prime with Aviva Silikat-Primer (4079) diluted 1:1 with water.

Stable mineral coatings

On coarsely porous, slightly sanding or absorbent surfaces, prime with Aviva Silikat-Primer (4079) diluted 1:1 with water.

Clay plasters:

Clean the substrate.

Base coating with Aviva Silikat-Primer (4079) diluted 1:1 with water.

Carry out a test coat under any circumstances and check for possible brown discolorations.

Substrate preparation	Glue-bound distempers: Wash thoroughly and prime with Aviva Tiefengrund WV (4074) diluted 1:1 with water. Avoid a glossy drying of Aviva Tiefengrund WV (4074).
COATING SYSTEM	
Primer coat	See substrate preparation
Intermediate coat	1 x Aviva Tiromin-Color (4066) undiluted or diluted with water to a maximum of 5 %.
Finishing coat	1 x Aviva Tiromin-Color (4066) undiluted or diluted with water to a maximum of 5 %.
ORDERING INFORMATION	
Size of trading unit	1 l, 3 l, 9 l, 15 l
Colour shades / Glosslevels Color4You	Colour shades can be obtained using the ADLER colour mixing system Color4you . Base paint(s): Aviva Tiromin-Color Basis W15 (4066000015) Aviva Tiromin-Color Basis W30 (4066000030) In order to ensure uniformity of the colour shade, use only material with the same batch number on a given surface. It is recommended to prepare a trial colour sample on the original substrate using the coating system selected in order to assess the final colour shade. Depending on the system, brilliant and intensive color shades may have a lower covering power. Hence, it is recommended to apply a preliminary coat of a comparable, opaque and pastel colour shade based on W15. In case of dark colour shades, mechanical stress may lead to bright stripes (writing effect). This is a product-specific characteristic of all matt wall paints. It does not affect the product quality and functionality.
Supplementary products	Aviva Silikat-Primer (4079) Aviva Tiefengrund WV (4074) Aviva Schimmelex chlorfrei (8312) Clean Multi-Entfetter (7233) Please refer to the corresponding technical data sheets of the products.
FURTHER DETAILS	
Durability / storage 	Min. 2 year(s) in the original sealed containers. Make sure the product is protected against moisture, direct sunlight, frost and high temperatures (above 30 °C). Close opened containers well and use up the content as soon as possible.
Technical specifications	VOC content of the ready-to-use mixture: Limit value according to Directive 2004/42/EC for Aviva Tiromin-Color (Cat A/a): 30 g/l. Aviva Tiromin-Color contains a maximum of 0 g/l VOC.
Declaration of ingredients according to VdL-RL 01	acrylic dispersions / potassium silicate / inorganic white and coloured pigments / water / surface additive / wetting agent

GiscodeBSW10

Safety information



The usual protective measures must also be observed when processing low-pollutant products.

The inhalation of paint aerosols during spray application must generally be avoided. This is ensured by the proper use of a respirator (combination filter A2/P2).

Wear safety goggles if there is a risk of splashing. If the product comes into contact with your eyes, rinse immediately with water.

Avoid contact with skin and eyes.

Aviva Tiromin-Color is highly alkaline.

Ensure good ventilation during application and drying.

During work, do not eat, drink or smoke.

Do not allow to enter drains, water courses or soil.

Only dispose of empty containers for recycling, liquid material residues can be disposed of as water-based paint waste, dried material residues as hardened paint or as household waste.

Further information on the subject of safety during transport, storage and handling as well as disposal can be found in the relevant safety data sheet. The current version can be accessed on the Internet at **www.adler-lacke.com**.
